

DESCRIZIONE DESCRIPTION

Carta a superficie naturale, fabbricata con il 50% di fibre di cotone e 50% di cellulosa E.C.F. Il prodotto è Acid Free, con riserva alcalina, a garanzia di lunga conservazione conformemente alla norma ISO 9706. Carta ideale per tutte le tenciche di stampa d'arte e grazie alla sua morbidezza e flessibilità per disegnare con tecniche secche.

Uncoated paper, made with 100% of E.C.F. bleached pulp manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706. Ideal paper for all printmaking techniques and thanks to its softness and flexibility it is ideal for drawing with dry techniques.

CONNOTAZIONI FEATURES



DATI TECNICI TECHNICAL DATA

CARATTERISTICHE PROPERTIES	METODOLOGIA METHOD	TARGET	MIN.	MAX.
Grammatura Grammage (g/m ²)	UNI EN ISO 536	250	245	255
VSA Bulk (cm ³ /kg)	UNI EN 534	1,6		
Assorbimento acqua Water absorptiveness (Cobb - g/m ²)	ISO 535	26	22	30
Ruvidità (Bendtsen) Roughness (Bendtsen) (ml/1')	ISO 8791/2	2000	1500	2500