

QCONNECT

Technical details

Grammage	ISO 536		75*
Thickness	ISO 534	mic.	99
Opacity	ISO 2471	%	92
CIE Whiteness	ISO 11475	%	160
Brightness	ISO 2470	%	106
Roughness	ISO 8791-2	ML/MIN	250 +- 50
Moisture	ISO 287	%	4,1

* Limit of Tolerance around +-4

Certifications

